

{material compatibility}

▶ Material	BXX	Effect compared to diesel fuel
Teflon	B100	Little Change
Nylon 6/6	B100	Little Change
Nitrile	B100	Hardness reduced 20%
Vitron A401-C	B100	Swell increased 18%
Vitron GFLT	B100	Little Change
Fluorosilicon	B100	Little Change
	B100	Swell increased 7%
Polyurethane	B100	Little Change in hardness
	B100	Swell increased 6%
Polypropylene	B100	Hardness reduced 10%
	B100	Swell increased 8-15%
Polyvinyl	B100	Much Worse
	B50	Worse
	B40	Worse
	B30	Worse
	B20	Comparable
Tygon	B10	Comparable
	B100	Worse

